

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>A01G 31/00</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 97/16961</b> <b>(43) International Publication Date:</b> 15 May 1997 (15.05.97)
<b>(21) International Application Number:</b> PCT/EP96/04996 <b>(22) International Filing Date:</b> 11 November 1996 (11.11.96) <b>(30) Priority Data:</b> 95203061.7 10 November 1995 (10.11.95) EP <b>(34) Countries for which the regional or international application was filed:</b> GB et al.  <b>(71) Applicant (for all designated States except US):</b> ROCK-WOOL/GRODAN B.V. [NL/NL]; Industrieweg 15, NL-6074 NH Melick-Herkenbosch (NL).  <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> DE GROOT, Jacob, Frank [NL/NL]; Elmpteweg 14, NL-6042 KK Roermond (NL). KNOP, Albert, Willem [NL/NL]; Haelerweg 61, NL-6085 EA Horn (NL). BOUWENS, Paul, Jacques, Louis, Hubert [NL/NL]; Veulenerbank 11, NL-6213 JR Maastricht (NL).  <b>(74) Agent:</b> PRINS, Hendrik, Willem; Arnold & Siedsma, Sweelinckplein 1, NL-2517 GK The Hague (NL).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> MINERAL WOOL PLANT SUBSTRATE  <b>(57) Abstract</b>  Mineral wool plant substrate comprising a coherent matrix of mineral wool, with 99.9 to 75 wt.% mineral wool and 0.1 to 25 wt.% organic substance, preferably the organic substance and clay are included in the matrix in the form of a pellet, more preferably in the form of a mixed pellet.		



**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

### MINERAL WOOL PLANT SUBSTRATE

The present invention relates to a mineral wool plant substrate, more in particular to a mineral wool plant substrate comprising a foreign material in order to improve the properties of the mineral wool plant  
5 substrate.

Mineral wool plant substrates for plant growth are well-known in the art and consist of a coherent matrix of mineral wool. This coherent matrix is formed by collecting a layer of mineral wool fibres provided with a  
10 curable binder, so that after curing the mineral wool fibres are substantially not displaceable relative to one another. If required for fast uptake of water this coherent matrix of mineral wool may be provided with a wetting agent.

15 As mineral wool may be used glass wool, stone wool, rock wool, or slag wool, and/or mixtures thereof.

The fibres may have an average diameter varying in between 1-10  $\mu\text{m}$ . For rock wool the fibre diameter is on average about 4  $\mu\text{m}$ .

20 The density of the coherent matrix of mineral wool may be between 10-200  $\text{kg/m}^3$ , in general in between 30-80  $\text{kg/m}^3$ .

Such a coherent matrix of mineral wool has a form retaining property, and is inherent due to the used  
25 inorganic starting materials. Furthermore, the water retaining capacity of this mineral wool plant substrates is very well controllable and predictable.

A disadvantage may be that during the plant growth initially the matrix reacts basic so that the pH  
30 increases.

It is a desire of growers to alleviate the aforementioned disadvantage, but above that to have the

possibility of controlling the exchange of nutrient cations.

Such properties are inherent to organic substances such as sphagnum and peat. But these materials are unsuitable for use in mineral wool plant substrates because during culture they loose structure, and by biological degradation of the organic substance the water retaining capacity changes such that less air is included within the material resulting in a acidification of the plant substrate.

The present invention provides a mineral wool plant substrate that combines the benificial properties of both mineral wool and organic substances while avoiding substantially the disadvantages of these two materials.

According to the present invention is provided a mineral wool plant substrate comprising a coherent matrix of mineral wool, with 99.9 to 75 wt% mineral wool and 0.1 to 25 wt% organic substance.

By including up to less than 25 wt% organic substance in a coherent matrix of mineral wool it is avoided that by the degradation of the organic substance substantially the structure and the water retaining capacity as well as the acidification occur. Above that, due to the presence of the organic substance the pH decrease is overcome due to the buffering property of the organic substance.

In order to avoid substantially the effect of biological degradation of the organic substance it is preferred that the substrate comprises 99.5 to 90 wt% mineral wool and 0.5 to 10 wt% organic substance, preferably 99.5 to 95 wt% mineral wool and 0.5 to 5 wt% organic substance.

Suitable organic substances are sphagnum and pressed peat as substantially biological non-degradable organic substances, and peat as such as a biological degrading organic substance. Using biologically degrading organic substances the mineral wool plant substrate provide further advantageous properties linked to the organic

substance, being the provision of a carbon source.

Further, due to the degradation of the organic substance are released growth hormones, humic acids and vitamins which are beneficial to plant growth, and further chelate  
5 forming compounds which keep slight or insoluble trace elements in the nutrient solution. Accordingly, the plant growth is optimally promoted.

It is emphasized that due to the use of peat the cat ion exchange capacity is optimally improved.

10 When it is desired to provide a mineral wool plant substrate having properties in between mineral wool and organic substance, it is worthwhile to partially substitute the organic substance by an inorganic substance being a natural clay. This clay does not  
15 provide a carbon source or growth hormones and chelate compounds but provides an intermediate cat ion exchange capacity. Accordingly, clay may substitute the organic substance for up to 99%, generally for up to 50%, preferably for up to 25%. This means that clay may be  
20 present in amounts between 0.01 to 9.9 wt%, generally in between 0.2 - 3%, such as 0.2 - 1 wt%.

Clay for substitution of the organic substance may comprise soil materials comprising hydrophilic particles. For instance a particle size below 20  $\mu\text{m}$ , belonging to  
25 the class of eroded minerals, such as clays, mixtures of clays with silt and sand having a clay fraction removable as sludge of at least 20%, and further bentonite, kaolin and the like. Particularly suitable are different naturally occurring types of clays of mixtures thereof,  
30 such as young sea clay. Examples are clays comprising 0-100%, preferably 10-50%, most preferably particles smaller than 20  $\mu\text{m}$ .

The use of clay provides another advantage when the organic substance is included in the matrix in the form  
35 of a pellet. Then, clay functions as a lubricating agent and as a material that reduces the compressability of the pellet. Accordingly, the amount of clay may be used in order to change the biodegradable character of the used

organic substance. Accordingly, peat which is normally biodegradable may be changed in partially to substantially bio-undegradable due to the addition of clay to the pellet. Accordingly, clay may inhibit or  
5 retard the biodegradation of the inorganic substance. The pellet may have a pellet size of about 2-10 mm.

Due to the presence of clay and of peat the concentration of spore elements in the water residing within the mineral wool matrix may be controlled, due to  
10 the sustained release of the cat ions temporarily stored within the organic substance and/or clay.

Examples of the mineral wool plant substrates according to the invention are the following.

Coherent matrices of mineral wool are provided  
15 having a density of about 50 kg/m<sup>3</sup> and an average fibre diameter of 4  $\mu$ m. During the production of these plant substrates organic substance in the form of peat is added during the formation of the matrix of mineral wool prior to binder curing. After passing through a curing oven a  
20 coherent matrix is obtained.

Plant substrates according to the invention have been prepared comprising 5, 10 and 20 wt% peat, the remainder being mineral wool.

Other mineral wool plant substrates have been  
25 prepared comprising 15 wt% peat, 5 wt% clay and 80 wt% mineral wool.

Another plant substrate according to the invention comprised 1 wt% sphagnum, 4 wt% clay and 95 wt% mineral wool.

30 The plant substrates have been used in the growth of plants and have shown an optimal control of the pH buffering, a sustained release of trace elements and of the water distribution. During culturing the biodegradation of peat and sphagnum resulted in a growth of mineral  
35 organisms providing growth promoting compounds to the plants.

CLAIMS

1. Mineral wool plant substrate comprising a coherent matrix of mineral wool, with 99.9 to 75 wt% mineral wool and 0.1 to 25 wt% organic substance.

2. Substrate as claimed in claim 1, comprising 99.5 to 90 wt% mineral wool and 0.5 to 10 wt% organic substance, preferably 99.5 to 95 wt% mineral wool and 0.5 to 5 wt% organic substance.

3. Substrate as claimed in claim 1, comprising clay substituting the organic substance for up to 99%.

4. Substrate as claimed in claim 3, comprising natural clay substituting organic substance for up to 50%, preferably for up to 25%.

5. Substrate as claimed in claim 1-4, wherein the organic substance comprises sphagnum, pressed peat.

6. Substrate as claimed in claim 1-5, wherein the organic substance is biologically degradable, comprising peat.

7. Substrate as claimed in claim 4-6, wherein the organic substance and clay are included in the matrix in the form of a pellet, preferably in the form of a mixed pellet.

# INTERNATIONAL SEARCH REPORT

National Application No

PCT/EP 96/04996

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 6 A01G31/00

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 A01G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 91 08662 A (ROCKWOOL INTERNATIONAL) 27 June 1991 see page 4, line 18 - page 5, line 15 ---	1-3
X	WO 93 18642 A (ISOVER SAINT GOBAIN) 30 September 1993 see claims 1,7,8 ---	1,2
X	WO 93 00797 A (GRODANIA) 21 January 1993 see claims 1,3 -----	1,2

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*&\* document member of the same patent family

Date of the actual completion of the international search

19 February 1997

Date of mailing of the international search report

03.03.97

Name and mailing address of the ISA  
European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+31-70) 340-3016

Authorized officer

Herygers, J



# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 96/04996

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9108662	27-06-91	AT-T- 109939	15-09-94
		AU-A- 6904691	18-07-91
		CA-A- 2070429	09-06-91
		DE-D- 69011689	22-09-94
		DE-T- 69011689	23-03-95
		EP-A- 0504206	23-09-92
		ES-T- 2060347	16-11-94
		FI-B- 96819	31-05-96
		JP-T- 5502159	22-04-93
		US-A- 5471786	05-12-95
-----			
WO-A-9318642	30-09-93	DE-A- 4208733	23-09-93
		AT-T- 140845	15-08-96
		AU-A- 3750293	21-10-93
		CA-A- 2132313	30-09-93
		DE-D- 69303895	05-09-96
		DE-T- 69303895	28-11-96
		EP-A- 0631466	04-01-95
		ES-T- 2090987	16-10-96
		JP-T- 7506965	03-08-95
		ZA-A- 9301315	20-10-93
-----			
WO-A-9300797	21-01-93	AU-A- 2311592	11-02-93
-----			

**THIS PAGE BLANK (USPTO)**